

# gloveon Ridley



## Latex Exam Gloves Powder Free, Standard Cuff

Just like this pioneer, GloveOn® Ridley has also conquered many different market segments. It continues to be the most popular choice of powder free latex glove in our range, offering unquantifiable aqueous latex proteins reading, and non-sensitising and non-irritant properties.



GloveOn® Ridley		
<b>Length (mm)</b>	≥ 230	
<b>Thickness Measurements (mm)</b>		
Palm (centre of Palm)	0.13 ± 0.03	
Finger (13mm ± 3mm from tip)	0.14 ± 0.03	
<b>Physical Properties</b>	<b>Before Ageing</b>	<b>After Ageing</b>
Tensile Strength (MPa)	≥ 18	≥ 16
Elongation (%)	≥ 650	≥ 500
<b>Inspection Levels &amp; AQL</b>	<b>Inspection Level</b>	<b>AQL</b>
Watertightness	G1	1.5
Physical Dimensions	S2	4.0
Tensile Strength	S2	4.0
Visual Inspection (Major)	S4	2.5
Visual Inspection (Minor)	S4	4.0
Particulate Residue	N = 5	≤ 2mg/glove
Protein Content	N = 3	≤ 50µg/g

### REORDER CODE

CHL11XS	X-SMALL
CHL11SS	SMALL
CHL11MM	MEDIUM
CHL11LL	LARGE
CHL11XL	X-LARGE

### FEATURES

- Fully textured
- Powder free
- Made with natural rubber latex
- Protein level ≤ 50µg/g
- Ambidextrous
- Standard cuff
- Natural colour

### PACKAGING

100 gloves per box for XS to XL  
10 boxes per carton

### REGULATORY COMPLIANCE

ARTG 127794, FDA 510(k), REACH,  
EC 1935/2004, CMDR SOR-98-282,  
EU 2016/425, MDD 93/42/EEC

### STANDARDS

AS/NZS 4011-1, ISO 11193-1, ASTM D5151,  
ASTM D3578, ASTM D6124, ASTM D5712,  
EN ISO 374-1 (Type B), EN 16523-1,  
EN 374 part 2, 4 & 5, EN 420,  
EN 455 part 1, 2, 3 & 4, EN 1186, EN 13130,  
CEN/TS 14234, ISO 10993 part 5 & 10,  
HACCP Certified

### MANUFACTURING ACCREDITATIONS

ISO 9001, ISO 13485, EN ISO 13485

\*Full test reports on Sensitisation Testing, Primary Skin Irritation and Residual Proteins Testing are available upon request.

A brand by



**Mun Australia**  
Toll free: 1800 456 837  
munglobal.com.au



Proud Supporter of  
Birthing Kit Foundation (Australia)



Protection Always On

MKG2019-052